

| Products | D10 [μm] | D90 [μm] | Bulk density [kg/m³] | Crush strength [psi] | Effective density [kg/m³] |
|-------------------------------------|-----------------|-----------------|--|-----------------------------|---|
| TRI-SPHERES [®] 120XL | 450 | 1.050 | 120 | < 725 | - |
| TRI-SPHERES [®] 200 | 100 | 340 | 200 | < 725 | 440 |
| TRI-SPHERES [®] 250 | 100 | 500 | 250 | - | 520 |
| TRI-SPHERES [®] 270 | 150 | 350 | 270 | - | 580 |
| TRI-SPHERES [®] 300 | 75 | 270 | 300 | 725 | 610 |
| TRI-SPHERES [®] 352 | 115 | 275 | 350 | 1.030 | 800 |
| TRI-SPHERES [®] 402 | 115 | 245 | 400 | 1.581 | 890 |
| TRI-SPHERES [®] 450 | 75 | 230 | 450 | 2.176 | 720 |
| TRI-SPHERES [®] 300S | 70 | 135 | 300 | 1.015 | 660 |
| TRI-SPHERES [®] 400S | 75 | 160 | 400 | 1.421 | 690 |
| TRI-SPHERES [®] 45XS ULTRA | 35 | 80 | 450 | 3.263 | 960 |

The stated values correspond to typical values and hence do not represent a specification.