

<b>Product</b>	<b>Appearance</b>	<b>Description</b>	<b>C-Content (%)</b>	<b>OAN (ml/100 g)</b>	<b>Density (g/cm³)</b>	<b>Average particle size* (µm)</b>
<b>LUVOMAXX® CF 602</b>	dark grey powder	natural composites of amorphous carbon and cryptocrystalline silica	85	55	1.40	3.7
<b>LUVOMAXX® CF 603</b>	dark grey powder		70	56	1.55	4.3
<b>LUVOMAXX® CF 704</b>	dark grey powder	natural composites of amorphous carbon and cryptocrystalline silica	15	29	2.50	4.5
<b>LUVOMAXX® CF 805</b>	greyish powder		8	24	2.30	6.0

\* laser diffractometry, wet measurement