

Product	Appearance	Properties and applications	Chlorine content (%)	Sulphur content (%)	Mooney ML (1+4) @ 100°C
CSM 20	Off-white irregular chips	Very good resistance to ozone, weathering, oil and chemicals; good low-temperature flexibility; rubber cements, adhesives, tapes, coatings	27 - 31	1.3 - 1.7	23 - 33
CSM 30	Off-white irregular chips	CSM grade with highest chlorine content; predestined for oil contact and flame retardant applications: anti-corrosion coatings, wires and cables, tubes, membranes	41 - 45	0.8 - 1.2	35 - 45
CSM 40 (3304)	Off-white irregular chips	Low-viscosity type of standard grade CSM 40; pls. see below	33 - 37	0.8 - 1.2	40 - 49
CSM 40 (3305)	Off-white irregular chips	General purpose grade CSM 40, good all-round properties reg. resistance to ozone, weathering, oil and chemicals; tubes, oil-seals, roll coverings, modification of other elastomers	33 - 37	0.8 - 1.2	50 - 60
CSM 45	Off-white irregular chips	Good abrasion resistance, very good weathering and heat resistance, moderate oil resistance; roofings, floorings, magnetic rubber parts, radiation shieldings	22 - 25	0.8 - 1.2	32 - 42
CSM 4085	Off-white irregular chips	High-mw CSM-Type 4085 suited for highly filled compounds; tubes, automotive hoses, seals / articles in contact with oil, cable sheathings, roll coverings	34 - 38	0.8 - 1.2	85 - 95