

Grade LUVOMAG®		Surface Activity BET area [m ² /g]	Bulk density [g/l]	Particle size d ₅₀ [µm]	Purity MgO content*
High activity grades	M 175	185	500	2	> 99,2 %
	M 074	160	400	3	> 98,7 %
	N50®	140	230	3	> 97,7 %
	N50® / light	140	205	3	> 97,7 %
	M 474	140	350	3	> 97,5 %
Medium activity grades	M 072	100	395	3	> 98,5 %
	M 440	50	200	3	> 98,0 %
Low activity grades	M 045	45	350	6	> 98,5 %
	M H30 light	40	220	3	> 97,8 %

*weight% on ignited basis

You can find an overview of our entire range of magnesium oxides [here](#).