

Product	Appearance	Density (g/cm ³)	Tensile strength (MPa)	Elong. at break (%)	Shore hardn. 10s, 23°C	Tear str. (kN/m)	Comp. set 22h@70°C (%)
TPV H721-70A	black granules	0.93	6.3	600	54 (A)	29	29
TPV 12-80A	black granules	0.95	13.7	622	90 (A)	93	46
TPV 721-93A	black granules	0.95	22.3	830	48 (D)	138	60
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395