

LUVOMAXX® BC Tread Grades

	ASTM Test method	N-115	N-121	N-134	N-220	N-234
Oil adsorption (ml/100g)	D 2414	113	131	127	114	125
Iodine no. (mg/g)	D 1510	160	121	142	121	120
Ash (% max.)	D 1506	0.5	0.5	0.5	0.5	0.5
Sieve residue 325 mesh (ppm max.)	D 1514	500	250	250	250	200
Nitrogen surface area (m²/g)	D 6556	137	122	143	119	119
Appearance	-	black pellets	black pellets	black pellets	black pellets	black pellets