

High Cis	Cis (%)	Viscosity ML (1+4) 100°C
NEOCIS BR 40	98	43
NEOCIS BR 60	98	63
Low Cis	Cis (%)	Viscosity ML (1+4) 100°C
INTENE 50	38	48
High Vinyl	Vinyl (%)	Viscosity ML (1+4) 100°C
EUOPRENE BR HV80	80	70