

	Appearance	Specific surface area BET [m <sup>2</sup> /g]	ash content [%]	Sieve residue > 45µm [%]	pH value
<b>LUVOMAXX® Silica HM 1160</b>	white powder	145 - 175	≤ 6	≤ 0.5	5 - 8
<b>LUVOMAXX® Silica HM 2160</b>	white granules	145 - 175	≤ 6	≤ 0.5	5 - 8
<b>LUVOMAXX® Silica HM 1170</b>	white powder	160 - 190	≤ 6	≤ 0.5	5 - 8
<b>LUVOMAXX® Silica HM 2170</b>	white granules	160 - 190	≤ 6	≤ 0.5	5 - 8
<b>LUVOMAXX® Silica HM 1180</b>	white powder	165 - 195	≤ 6	≤ 0.5	5 - 8
<b>LUVOMAXX® Silica HM 2180</b>	white granules	165 - 195	≤ 6	≤ 0.5	5 - 8