

LUVOMAXX® BC Carcass Grades

	ASTM Test method	N-539	N-550	N-650	N-660	N-772
<b>Oil adsorption (ml/100g)</b>	D 2414	111	121	122	90	65
<b>Iodine no. (mg/g)</b>	D 1510	43	43	36	36	30
<b>Ash (% max.)</b>	D 1506	0.5	0.5	0.5	0.5	0.5
<b>Sieve residue 325 mesh (ppm max.)</b>	D 1514	100	200	250	250	500
<b>Nitrogen surface area (m<sup>2</sup>/g)</b>	D 6556	38	40	36	35	32
<b>Appearance</b>	-	black pellets	black pellets	black pellets	black pellets	black pellets