

Product	Appearance	Properties and applications	Volatile matter (%)	TG	Mooney ML (1+4) @ 100°C
ISOGRI P™	Bales	<ul style="list-style-type: none"> • Very good mechanical damping/ sound damping properties • Improved grip and wet grip • Straightforward co-vulcanization in blends with NR and SBR. Car and truck tyres, soles for climbing, walking and safety boots, sailing shoes, golfing items, car sports seats, insulation materials for cars, machinery as well as household and office appliances 	< 0.5	- 10 °C	65 - 75
