

Product	Appearance	Active ingredient	Gas yield (ml/g)	Decomp. temperature (°C)
LUVOPOR® AT 6100	Yellow powder	System, based on azodicarbonamide	280	150
LUVOPOR® 9509	Yellow powder	ZnO-activated azodicarbonamide	165	190