

Grade LUVOMAG®	Origin		Purity [wt %]					Remarks
	Syn.	Nat.	Mg(OH) <sub>2</sub>	CaO	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	Lol	
<b>H 002</b>	•		99.2			0.02		BET 10 m <sup>2</sup> /g
<b>H 015</b>	•		99.0	0.45	0.12	0.04		BET 10 m <sup>2</sup> /g
<b>H 110</b>	•		96.5	0.70	0.10	0.07	31.5	
<b>H 257</b>		•	95.3	2.1	3.7	0.50	31.0	Coated and var. milled grades available
<b>Brucite</b>		•	92.5	3.0	5.5	0.35	30.0	Various granular and milled grades available

Lol: loss on ignition.

Further grades and property details available upon request.